

BURNT REFRACTORY CERAMIC PRODUCT AND MIXTURE FOR ITS
MANUFACTURE

CLAIMS

1. A burnt refractory ceramic product with the following mineralogical phases:
 - 1.1 70-98% by weight of a stoichiometric $\text{MgO-Al}_2\text{O}_3$ spinel
 - 1.2 1-15% by weight of forsterite
 - 1.3 1-15% by weight of periclase
 - 1.4 Up to 10% by weight of other,wherein the total is 100% by weight.
2. The product according to Claim 1, with the following mineralogical phases:
 - 2.1 70-97% by weight of a stoichiometric $\text{MgO-Al}_2\text{O}_3$ spinel
 - 2.2 1-10% by weight of forsterite
 - 2.3 1-10% by weight of periclase
 - 2.4 1-10% by weight of ZrO_2 and/or at least one Ca-Al oxide phase
3. The product according to Claim 1, with a density $> 3.35 \text{ g/cm}^3$.
4. A mixture for manufacturing a refractory product according to any one of Claims 1-3, which comprises the following components:
 - 4.1 70-98% by weight of a non-stoichiometric $\text{MgO-Al}_2\text{O}_3$ spinel
 - 4.2 2-30% by weight of mullite
 - 4.3 Up to 10% by weight of other,

f

wherein the total is 100% by weight.

5. The mixture according to Claim 4, in which the mullite consists of sinter mullite.
6. The mixture according to Claim 4, wherein the components have a grain size $< 50 \mu\text{m}$.
7. The mixture according to Claim 4, in which the components are prepared by mixing to granules.
8. The mixture according to Claim 4, with a proportion of up to 10% by weight of ZrO_2 or a component containing ZrO_2 .
9. The mixture according to Claim 4, wherein the non-stoichiometric $\text{MgO-Al}_2\text{O}_3$ spinel has the following compositions:

Al_2O_3 : 58-70% by weight

MgO : 29-40% by weight

secondary constituents: $< 5\%$ by weight

wherein the total is 100% by weight.

h